

TECHNICAL INFORMATION

2150 KOPENHAGEN


TECHNICAL SPECIFICATIONS ACCORDING TO EN 1307

constructie	<i>construction</i>	ISO 2424	1/10" cut pile
poolmateriaal	<i>yarn content</i>	ISO 2424	100% PA 6
rug	<i>backing</i>	ISO 2424	Ceneva® Actionbac®
gebruiksklasse	<i>suitability</i>	EN 1307	23 / 32 medium contract use
poolgewicht	<i>pile weight</i>	ISO 2424	1325 gr/m ²
totaal gewicht	<i>total weight</i>	ISO 8543	2000 gr/m ²
pooldikte	<i>pile height</i>	ISO 1766	4.7 mm
totaal dikte	<i>total thickness</i>	ISO 1765	7.4 mm
noppental	<i>tuft density</i>	ISO 1763	205,000 tufts/m ²
breedte	<i>width</i>	CEN/TS 14159	ca. 4 m
warmte-doorlaatweerstand	<i>thermal resistance</i>	ISO 8302	0.12 m ² K/W
brandklasse	<i>flammability</i>	ISO 13501-1	Cfl-S1
structure	<i>Konstruktion</i>	ISO 2424	1/10" cut pile
composition	<i>Polmaterial</i>	ISO 2424	100% PA 6
dossier	<i>Beschichtung</i>	ISO 2424	Ceneva® Actionbac®
classement d'usage	<i>Zusatzeignung</i>	EN 1307	23 / 32 medium contract use
poids de velours	<i>Poleinsatzgewicht</i>	ISO 2424	1325 gr/m ²
poids total	<i>Gesamtgewicht</i>	ISO 8543	2000 gr/m ²
hauteur du velours	<i>Polschichtdicke</i>	ISO 1766	4.7 mm
épaisseur totale	<i>Gesamtdicke</i>	ISO 1765	7.4 mm
densité	<i>Noppenzahl</i>	ISO 1763	205,000 tufts/m ²
dimensions	<i>Breite</i>	CEN/TS 14159	ca. 4 m
résistance thermique	<i>Wärmedurchlasswiderstand</i>	ISO 8302	0.12 m ² K/W
comportement au feu	<i>Brandverhalten</i>	ISO 13501-1	Cfl-S1

COLOURS

134 Basil	145 Red Pepper	165 Rioja
139 Squirrel	149 Desman	169 Mist
143 Iron Oxide	161 Delpinium	181 River
144 Loam	163 Coffee	199 Magma

PRODIS RATING AND INFORMATION



PRODIS: AB0B7A2A

DOP: 1025-121403



CONTACT INFORMATION

THE NETHERLANDS
(HEAD OFFICE)
NIJVERHEIDSTRAAT 39
NL - 8281 JD GENEMUIDEN
+31 (0)38 385 22 11
INFO@EDELGROUP.NL
WWW.EDELGROUP.NL

UNITED KINGDOM
(UK SALES ONLY)
+44 (0)1422 37 44 17
+44 (0)1422 37 12 26
SALES@EDELTELENZOCARPETS.CO.UK
WWW.EDELTELENZOCARPETS.CO.UK

geproduceerd door / manufactured by
fabriqué par / hergestellt durch

edelgroup®
since 1918

Alle technische specificaties zijn onderhevig aan productietoleranties. Voor alle voorwaarden en onderhoudsadvies verwijzen wij u graag naar onze website.

All specifications are subject to normal manufacturing tolerances. For all Terms & Conditions, care and maintenance, please visit our website.

Toutes les spécifications techniques sont sujet aux tolérances de fabrication. Merci de consulter notre website pour toutes informations et les conseils d'entretien.

Alle technische Daten unterliegen Produktionstoleranzen. Bedingungen und Pflegeempfehlungen finden Sie auf unserer Website.